

AES-300RP Product Data Sheet

Description and Physical Properties

AES-300RP is a high float, polymer modified, medium setting anionic water-based asphalt emulsion for use in recycling and rehabilitating asphalt and aggregate mixtures. The high float gives the emulsion residue a gel structure which resists flow and drain-down, the polymer gives elasticity and durability, and the rejuvenator oils aid in the recycling of aged pavements.

Physical Properties:

- Boiling Point (F): 212°F
- Specific Gravity (H2O=1): 1.01
- Percent Volatile: 0
- Solubility In Water: Soluble
- Appearance And Odor: Brown Liquid, Faint Petroleum Odor

Recommended Use

AES-300RP can be mixed cold or warm at a central plant, with a portable pugmill at the job site or in-place on the roadway. The mixed material may be used immediately, or stockpiled for later use. It may be placed with a paver or worked onto the pavement with a blade or reclaimer.

Specifications:

Property	Test Procedure	Min	Max
Viscosity, Saybolt Furol, 77°F, sec	T72	75	400
Sieve test, %	T59	–	0.1
Storage stability, 1 day, %	T59	–	1
Distillation test:	T59 Modified		
Residue by distillation, % by wt.		65	–
Oil distillate, % by volume of emulsion		–	7
Tests on residue from distillation:			
Penetration, 77°F, 100 g, 5 sec.	T49	300	–
Solubility in trichloroethylene, %	T44	97	–
Ductility, 77 °F, 5 cm./min., cm.	T51	50	
Float test, 140°F, sec.	T50	1,200	–

Storage and Handling

The water-based emulsion should not be exposed to freezing temperatures or overheating. The emulsion is a chemically stabilized system, so care should be taken not to upset the chemical balance with contamination by chemicals, over-exposure to air, or adverse mechanical or thermal conditions. Before being filled, tanks and trucks should be examined for possible contaminants. Recommended use and storage temperatures are given in the table.

Recommended Temperatures	Min	Max
Storage	120°F	180°F
Application	120°F	160°F

Martin Asphalt Quality

Through Martin Asphalt, you get **Everything Asphalt**—a full range of products. In addition, you receive technical assistance in selecting the right materials and application. The company's AASHTO Certified Laboratory makes sure the products meet your specifications. And your products are delivered both on spec and on time via Martin's Gulf Coast network of production plants, storage facilities and transportation fleet including ocean-going and inland barges, rail cars and tanker trucks. For more information, contact us.