CMS-2 Product Data Sheet



Description and Physical Properties

CMS-2 is a medium setting cationic water-based asphalt emulsion for use in cold and warm asphalt and aggregate mixtures, base stabilization, and full depth reclamation. Physical Properties:

• Boiling Point (F): 212°F

• Specific Gravity (H20=1): 1.01

• Percent Volatile: 0

Solubility In Water: Soluble

• Appearance And Odor: Brown Liquid, Faint Petroleum Odor

Recommended Use

CMS-2 can be mixed cold or warm at a central plant, with a portable pugmill at the job site or in-place on the roadway. The mixed material may be used immediately, or stockpiled for later use. It may be placed with a paver or worked onto the pavement with a blade or reclaimer.

Specifications Conforms to Texas Department of Transportation Specifications-Item 300.2.4 Table 8:

Property	Test Procedure	Min	Max
Viscosity, Saybolt Furol, 122°F, sec	T72	100	300
Sieve test, %	T59	_	0.1
Coating ability and water resistance:	T59		
dry aggregate/after spray		Good/I	air
wet aggregate/after spray		Fair/F	air
Particle charge	T59	Positive	
Distillation test:	T59		
Residue by distillation, % by wt.		65	_
Oil distillate, % by volume of emulsion		_	7
Tests on residue from distillation:			
Penetration, 77°F, 100 g, 5 sec.	T49	120	200
Solubility in trichloroethylene, %	T44	97.5	_
Ductility, 77°F, 5 cm/min., cm	T51	100	_

Storage and Handling

The water-based emulsion should not be exposed to freezing temperatures or overheating. The emulsion is a chemically stabilized system, so care should be taken not to upset

the chemical balance with contamination by chemicals, overexposure to air, or adverse mechanical or thermal conditions. Before being filled, tanks and trucks should be examined for possible contaminants. Recommended use and storage temperatures are given in the table.

Recommended Temperatures	Min	Max
Storage	120 ⁰ F	180 ⁰ F
Application	120 ⁰ F	160 ⁰ F

Martin Asphalt Quality

Through Martin Asphalt, you get **Everything Asphalt**—a full range of products. In addition, you receive technical assistance in selecting the right materials and application. The company's AASHTO Certified Laboratory makes sure the products meet your specifications. And your products are delivered both on spec and on time via Martin's Gulf Coast network of production plants, storage facilities and transportation fleet including ocean-going and inland barges, rail cars and tanker trucks. For more information, contact us.

www.MartinAsphalt.com

EVERYTHING ASPHALT

800-662-0987

Product Date Sheet - CMS-2 doc rev. 08/30/16