

RC-250 Product Data Sheet



Description and Physical Properties

Rapid curing cutback asphalts are blends of selected asphalts and light petroleum solvents. RC-250 is designed for use as a spray-applied binder for cool temperature seal coats.

Specifications Conform to Texas Department of Transportation Specifications-Item 300.2:

Property	Test Procedure	Type-Grade	
		RC-250	
		Min	Max
Kinematic viscosity, 140°F, cSt	T 201	250	400
Water, %	T 55	–	0.2
Flash point, T.O.C., °F	T 79	80	–
Distillation test:	T 78		
Distillate, percentage by volume of total distillate to 680°F			
to 437°F		40	75
to 500°F		65	90
to 600°F		85	–
Residue from distillation, volume %		70	–
Tests on distillation residue:			
Penetration, 100 g, 5 sec., 77°F	T 49	80	120
Ductility, 5 cm/min., 77°F, cm	T 51	100	–
Solubility in trichloroethylene, %	T 44	99.0	–
Spot test	Tex-509-C		Neg.

Storage and Handling

Before being filled, tanks and trucks should be examined for possible contaminants. Cutback asphalts should be kept away from ignition sources.

Storage and Application Temperatures

Type-Grade	Application		Storage Maximum (°F)
	Recommended Range, °F	Maximum Allowable (°F)	
RC-250	125–180	200	200

Martin Asphalt Quality

Through Martin Asphalt, you get **Everything Asphalt**—a full range of products. In addition, you receive technical assistance in selecting the right materials and application. The company's AASHTO Certified Laboratory makes sure the products meet your specifications. And your products are delivered both on spec and on time via Martin's Gulf Coast network of production plants, storage facilities and transportation fleet including ocean-going and inland barges, rail cars and tanker trucks. For more information, contact us.

www.MartinAsphalt.com

EVERYTHING ASPHALT

800-662-0987

Product Date Sheet – RC-250.doc rev. 07/25/16